

Water-based hydrophobic preparation, giving the 'wet-look' effect and not increasing slipperiness of surface.

Reduces the absorbability of the substrate

Enhances resistance to dirt and efflorescence

HBp-2 is a high performance, all-purpose patio sealer formulated for porous external natural stone surfaces, such as slate, terracotta, York stone, quarry tiles, sandstone, limestone, concrete and many more stone types.

It reduces the absorbability of the substrate – ensures protection against precipitation water and penetration of harmful chemical compounds dissolved in water into the material structure. It increases the resistance of the impregnated surface to dirt, efflorescence and the development of biological contamination.

Alkali-resistant, durable – UV-resistant, solvent-free. It does not degrade the properties of the protected material in terms of gas and water vapor diffusion; the pores remain open.

Application area

Natural stone surfaces, such as slate, terracotta, York stone, quarry tiles, sandstone, limestone, concrete

It can be used indoors and outdoors,

for old and new surfaces.

Application:

PRIOR APPLICATION:

Before application, the surface should be cleaned of dirt, dust, patina, loose elements, salt efflorescence and residues of paint coats.

Any adjacent surfaces not being treated with the product must be protected.

Never apply to wet surfaces. The product can be used on slightly damp surfaces; nonetheless, please ensure that the surface to be treated is as dry as possible.

At the time of application, surface should not be displayed in direct sunlight and rainfalls.

Note. Impregnation should not be performed on surfaces with high salinity, as this may lead to intensification of the crystallization process of construction salts and destruction of the substrate material.

APPLICATION INSTRUCTION:

HBp-1 is a ready to use product. DO NOT DILUTE.

May be applied using low pressure spray, brush or roller.

Apply the product generously and evenly on the entire area until the surface is saturated. Repeat the action several times depending on attributes and porosity of the surface by the "wet on the wet" method.

Subsequent applications MUST be applied "wet on wet" within 10 minutes of previous application. Do not allow the substrate to dry between application.

Depending on the properties and porosity of the protected substrate, the above procedure should be repeated 2 or 3 times.

During works and immediately after their completion, the freshly impregnated surfaces should be protected against direct sunlight and precipitation for a minimum of 5 hours.

Comments and recommendations

Do not allow the applied product to dry between applications.

Do not apply during rain or frost and when surface and air temperature is $< 5^{\circ}\text{C}$ and $> 30^{\circ}\text{C}$.

All surfaces must be treated to saturation in 1-3 applications "wet on wet" applied, to ensure 100% product efficacy. This varies with substrate, and treating a small trial area is recommended to calculate true consumption.

This information constitutes the basic guidelines for the use of the product and does not release from the obligation to perform work in accordance with the principles of art of the construction, conservation guidelines and health and safety regulations.

Do not apply during rain or frost and when surface and air temperature is $< 5^{\circ}\text{C}$ and $> 30^{\circ}\text{C}$.

Before application, we recommend testing the product on a small, unexposed area.

Warnings:

KEEP OUT OF REACH OF CHILDREN & PETS. ATTENTION CAUSTIC PRODUCT

The product contains: siloxanes and silicones, 3-[(2-aminoethyl)amino]propyl Me, di-Me; and the preservative 2-methyl-2H-isothiazol-3-one

Technical specifications

Product density: approx. $1.1 \text{ kg} / \text{dm}^3$

PH: approx. 7

Odour: characteristic

Colour: milky white, colourless after drying - giving the effect of a wet substrate, transparent

Rain resistance: 5-6 hours

Water absorption coefficient: $W_d < 0.1 \text{ kg} / \text{m}^2 \times h_1 / 2$ or $< 7.5\%$ acc. PN-EN 1504-2 / EN 13580 /

Water vapor diffusion resistance: $S_d = 0.0 \text{ [m]}$

Alkali resistance - measured with water absorption according to PN-EN 1504-2 / EN 13580 $< 10\%$

Penetration depth: $> 5 \text{ mm}$, measured according to EN 14630

Drying rate factor class 2 to 1 / depending on the degree of absorption / water absorption substrate, measured according to EN 13579

1L covers approx. $5\text{-}11 \text{ m}^2$

Available packaging

1L/5L

Expiry date: Up to 36 months of storage at temperatures $> + 5^{\circ}\text{C}$ to $< 30^{\circ}\text{C}$, in original unopened manufacturer's packaging. Water-based product = it freezes at temperatures $< 0^{\circ}\text{C}$.